













	Creation 30	Creation 40	Creation 40 Clic	Creation 40 Clic Acoustic	Creation 55			Creation 55 Clic	Creation 55 Clic Acoustic		
More technical datas											
<b>Description / Beschrijving / Descripción / Descrição / Descrizione</b>					Arte	Trend	Design				
Total Thickness / Totale dikte / Espesor total / Espessura total / Spessore totale	EN ISO 24346	mm	2.00	2.00	4.50	5.50	2.50	5.00	6.00		
Thickness of the wearlayer / Dikte van de slijdlaag / Espesor capa de uso / Espessura camada de desgaste / Spessore strato di usura	EN ISO 24340	mm	0.30	0.40	0.45	0.45	0.55	0.55	0.55		
Weight / Gewicht / Peso / Peso / Peso	EN ISO 23997	sqm	3460	3430	7118	7229	3850	4410	7781	8024	9480
Size / Afmetingen / Dimensiones / Dimensões / Dimensione			184.15x1219.2 15 / 3.36	184.15x1219.2 21 / 4.71	212x1238.8 8 / 2.10	212x1238.8 8 / 2.10	184.15x1219.2 15 / 3.36	184.15x1219.2 (EIR) 15 / 3.36	212x1238.8 7 / 1.84	212x1238.8 7 / 1.84	125x750 16 / 1.5
Number of planks & tiles / sqm per box Número de planchas / baldosas y metros cuadrados por caja Número de tábuas / ladrilhos e m² por caixa Numero e mq di piastre / doghe per box	EN ISO 24342	mm	230x1500 11 / 3.80	230x1500 13 / 4.49	239.6x1460.8 7 / 2.45	239.6x1460.8 6 / 2.10	152.4x762 33 / 3.82	230x1500 (EIR) 9 / 3.11	239.6x1460.8 6 / 2.10	239.6x1460.8 5 / 1.75	125x750 16 / 1.5
			457.2x914.4 9 / 3.76	457.2x914.4 11 / 4.6	388.8x728.7 7 / 1.98	388.8x728.7 7 / 1.98	496.5x996.5 8 / 3.96	457.2x914.4 9 / 3.76	609.6x609.6 9 / 3.35	388.8x728.7 6 / 1.70	388.8x728.7 6 / 1.70
			609.6x609.6 9 / 3.35				609.6x609.6 9 / 3.35	914.4x914.4 5 / 4.18			

Classification Classificatie / Clasificaciones / Classificações / Classificazioni									
Norm/Product Specification / Technische eigenschappen / Normas / Normas / Norma prodotto	-	-	EN ISO 10582		EN ISO 10582			EN ISO 10582	
European Classification / Europese classificatie / Clasificación europea / Classificação Europeia / Europea	EN ISO 10874	class	23 - 31		23 - 32			33 - 42	
Fire Rating / Brand classificatie / Fuego / Fogo / Reazione al fuoco	EN 13 501-1	class	Bfl-s1		Bfl-s1			Bfl-s1	
Static Electrical Propensity / Elektrische eigenschappen / Comportamiento electrostático / Comportamento electrostático / Resistenza elettrica	EN 1815	kV	< 2		< 2			< 2	
Slip Resistance Wet / Anti-slip / Deslizamiento húmedo / Escorregamento húmido / Scivolosità umida <sup>1)</sup>	DIN 51130	class	R10		R10			R10	

Performances / Testresultaat / Cualidades técnicas / Performances / Caratteristiche tecniche										
Wear Resistance / Slijtvastheid / Abrasión / Abrasão / Resistenza all'abrasione	EN 660.2	mm³	≤ 2.0		≤ 2.0			≤ 2.0		
Wear Group / Groep slijtvastheid / Grupo de abrasión / Grupo de abrasão / Gruppo di abrasione	-	-	T		T			T		
Type Binder content / Contenido en ligante / Conteúdo em ligante	EN ISO 10582	type	I		I			I		
Room Impact / Loopgeluid / Rumore al calpestio / Sonoridade ao andar	NF S 31074	dB	77	77	79	79	77	79	79	
Impact sound insulation / Geluidsisolatie / Acústica / Isolamento acústico	EN ISO 717-2	dB	4	4	4	19	4	4	19	
Dimensional stability (norm) / Maatvastheid (norm) / Estabilidad Dimensional (Exigencia) / Estabilidade dimensional (normalização) / Stabilità dimensionale (requisito normativo)	EN ISO 23999	%	≤ 0.25	≤ 0.25	≤ 0.15	≤ 0.15	≤ 0.25	≤ 0.15	≤ 0.15	
Dimensional stability (average measured value) / Maatvastheid (gemeten gemiddelde waarde) / Estabilidad Dimensional (Valor medio) / Estabilidade Dimensional (Valor medio) / Stabilità dimensionale (rilevata)	-	%	≈ 0.10	≈ 0.10	≈ 0.05	≈ 0.05	≈ 0.10	≈ 0.05	≈ 0.05	
Castor chair test / Rolweerstand bureaustoelen / Determinación del efecto de una silla con ruedas / Resistência a cadeiras de rodas / Resistenza al passaggio di sed (Type W)	ISO 4918	-	OK		OK			OK		
Thermal Conductivity / Thermische weerstand / Conductivité térmica / Contutividade térmica / Resistenza termica / Värmeledningsmotstånd / Varmemotstand	EN ISO 10456	W/(m.K)	0.25		0.25			0.25		
Thermal resistance	EN ISO 10456	M².K/W	0.008		0.008		0.008	0.008	0.008	
Colour Fastness / Lichttechtheid / Resistencia a la luz / Estabilidade das cores / Solidità alla luce	EN 20 105 - B02	degree	≥ 6		≥ 6			≥ 6		
Surface Treatment / Oppervlaktebehandling / Tratamiento de superficie / Tratamento de superficie	-	-	ProtecShield™		ProtecShield™			ProtecShield™		
Chemical Products Resistance / Chemische bestendigheit / Resistencia a los productos químicos / Resistência aos produtos químicos / Resistenza ai prodotti chimici	EN ISO 28987	-	OK		OK			OK		
<b>Environment / Umwelt / Medio ambiente / Ambiente / Ambiente</b>										
Recycled content (average) Anteil Recyclingmaterial Durchschnitt / Contenido reciclado (media) / Conteúdo reciclado (média) / Contenuto riciclato (medio) - %	-	%	35	35	33	33	20	35	33	33
Recyclability / Wiederverwertbarkeit / Reciclabilidade / Reciclabilidade - %	-	%	100		100			100		
<b>Health / Salud / Saúde / Salute</b>										
TVOC after 28 days / TVOC (28 dagen) / TVOC (28 dias) / TVOC (28 dias) / TVOC (28 giorni) / TVOC (28 dagen) / TVOC (28 dager)	ISO 16000-6	micrograms / m³	< 10		< 10			< 10		
Floorscore®	-	-	OK		OK			OK	-	
SCS Global Certification	-	-	-		OK			OK	-	

CE Marking / Eg_conformiteitsmerk / Marca De Conformidad CE / Marca DE Conformidade CE / Marcatura CE Di Conformita									
	EN 14041	-							

## we care / we act our commitments for 2030



**climate**

**-30% CO<sub>2</sub>**  
scopes 1, 2, 3 in tons eq CO<sub>2</sub>, vs 2019.  
Science Based Targets<sup>(1)</sup>



**resources**

**75%** biobased, mineral & recycled<sup>(2)</sup>

**30%** recycled content<sup>(3)</sup>



**circularity**

**65,000** tons of waste treated<sup>(4)</sup>

**45%** looselay<sup>(5)</sup>



**health & well-being**

**100%** of our products perform better than Indoor Air Quality standards<sup>(6)</sup>

**95%** sales covered by EPDs<sup>(7)</sup>



**people**

**30%** women<sup>(8)</sup>

**40%** internal mobility<sup>(9)</sup>

**Towards 0** accident<sup>(10)</sup>

**More details:** 1. Scopes 1, 2 & 3, in absolute value, market-based. Trajectory approved by SBTi (Science Based Targets Initiative). 2. Origin of raw materials for the entire Floor & Wall portfolio, on average, by weight, including 15% virgin salt, a primary element in vinyl manufacturing. Compared to 71% in 2024. 3. Average content in the Floor & Wall vinyl portfolio, by weight. Compared to 21% in 2024. 4. Recycled in our factories and recycling units. Compared to 59 040 tons in 2024. 5. % of floor activity with non-glued products, easy to remove, easy to re-use. Compared to 40% in 2024. 6. 100% of vinyl and linoleum sold to the building market below 100 micrograms / m³ (TVOC 28 days). 7. % of Floor & Wall activity covered by Environmental Product Declarations (EPD). Compared to 44% in 2024. 8. % women in our global workforce and among our managers. Compared to respectively 26% and 27% in 2024. 9. % job openings filled with internal hires worldwide. Compared to 25% in 2024. 10. Towards 0 accident: Lost time accident per million hours worked: below 3 vs 8.9 in 2024, for Gerflor employees worldwide.

(1) Ramp test with oil - **IMPORTANT:** The information contained in this document is valid from 01/09/2025 and is subject to change at any time without notice. In the context of constantly changing technology, our customers are responsible, prior to any use, for checking with us that this document is the version in force.

