




| DESCRIPTION  |                | TREND              |   |                          |                          |                          |
|--|----------------|--------------------|---|--------------------------|--------------------------|--------------------------|
| Total Thickness  | EN ISO 24346   | mm                 | 2   |                          |                          |                          |
| Thickness of the wearlayer   | EN ISO 24340   | mm                 | 0,40  |                          |                          |                          |
| Weight   | EN ISO 23997   | g/m <sup>2</sup>   | 3180  |                          |                          |                          |
| Size   | EN ISO 24342   | mm                 | 457,2 x 914,4   | 609,6 x 609,6            | 184,15 x 1219,2          | 230,0 x 1500,0           |
| Number of planks /tiles and sqm per box  | -              | -                  | 11 / 4,60 m <sup>2</sup>  | 13 / 4,83 m <sup>2</sup> | 21 / 4,71 m <sup>2</sup> | 13 / 4,49 m <sup>2</sup> |
| CLASSIFICATION   |                |                    |   |                          |                          |                          |
| Norm/Product Specification   | -              | -                  | EN ISO 10582  |                          |                          |                          |
| European Classification  | EN ISO 10874   | class              | 23 - 32 - 41  |                          |                          |                          |
| Fire Rating  | EN 13 501-1    | class              | Bfl-s1  |                          |                          |                          |
| Static Electrical Propensity   | EN 1815        | kV                 | < 2   |                          |                          |                          |
| Slip Resistance Wet  | DIN 51 130     | class              | R10   |                          |                          |                          |
| PERFORMANCES   |                |                    |   |                          |                          |                          |
| Wear Resistance  | EN 660.2       | mm <sup>3</sup>    | < 2,0   |                          |                          |                          |
| Wear Group   | -              | group              | T   |                          |                          |                          |
| Type Binder content  | ISO 10582      | group              | I   |                          |                          |                          |
| Room Impact  | NF S 31074     | dB                 | 77  |                          |                          |                          |
| Impact sound insulation  | EN ISO 717-2   | dB                 | 4   |                          |                          |                          |
| Dimensional stability (norm)   | EN ISO 23999   | %                  | ≤ 0,25  |                          |                          |                          |
| Dimensional stability (average measured value)                                     | -              | %                  | ≤ 0,10  |                          |                          |                          |
| Residual Indentation   | EN ISO 24343-1 | mm                 | ≤ 0,10  |                          |                          |                          |
| Castor chair test  | ISO 4918       | -                  | OK  |                          |                          |                          |
| Thermal Conductivity   | EN ISO 10456   | W/(m.K)            | 0,25  |                          |                          |                          |
| Colour Fastness  | EN ISO 105-B02 | degree             | ≥ 6   |                          |                          |                          |
| Surface Treatment  | -              | -                  | Protecshield™   |                          |                          |                          |
| Chemical Products Resistance   | EN ISO 26987   |                    | OK  |                          |                          |                          |
| ENVIRONMENT / INDOOR AIR QUALITY   |                |                    |   |                          |                          |                          |
| TVOC after 28 days   | ISO 16000-6    | µg/ m <sup>3</sup> | < 10  |                          |                          |                          |
| CE MARKING   |                |                    |   |                          |                          |                          |
|  | EN 14041       |                    |  |                          |                          |                          |
|  |                |                    |  |                          |                          |                          |